

**Listing Of The Claims**

This listing of claims will replace all prior versions, and listings, of claims in the application:

**Listing of Claims:**

1. (Currently amended) A reheat stretch blow molded multilayer container comprising:  
a first layer defining an outermost layer of the container and comprising polypropylene;  
and  
a second layer comprising an oxygen barrier material, directly adjacent to said first layer;  
at least one of said first and second layer further comprises an adhesive to facilitate  
bonding between the first and second layers, the container having been biaxially stretched and  
having a haze value of less than approximately 29% measured through a section of the container  
having a total thickness of greater than approximately 15 mils.
2. (Previously Presented) The container of claim 1 the first layer comprising the adhesive  
wherein said adhesive comprises approximately 0.01% to 0.20% maleic anhydride.
3. (Previously Presented) The container of claim 1 the first layer comprising the  
adhesive wherein said adhesive comprises approximately 0.015% maleic anhydride.
4. (Cancelled)
5. (Previously Presented) The container of claim 1 wherein said container has a haze  
value of approximately 10%-12% measured through a section of the container having a total  
thickness of greater than approximately 15 mils.
6. (Original) The container of claim 1 wherein said second layer comprises EVOH.
7. (Previously Presented) The container of claim 1 wherein said second layer comprises  
nylon.
8. (Original) The container of claim 1 wherein said second layer comprises nylon 6.
9. (Original) The container of claim 1 wherein said second layer comprises nylon 6/66.
10. (Previously Presented) The container of claim 1, the adhesive being maleic  
anhydride.

11. (Previously Presented) The container of claim 1 further comprising a third layer comprised of polypropylene adjacent to the second layer.

12. (Previously Presented) The container of claim 11, the adhesive in one of the first and second layers being located in the first layer and the third layer further comprising an adhesive.

13. (Previously Presented) The container of claim 12, the adhesive in the first and third layers being maleic anhydride.

14. (Previously Presented) The container of claim 11, the third layer defining an innermost layer.

15. (Previously Presented) The container of claim 14, the third layer being bonded directly to the second layer.

16. (Previously Presented) The container of claim 7, the second layer further comprising cobalt.

17. (Currently amended) A reheat stretch blow molded multilayer container comprising:  
a first layer defining an innermost layer of the container and comprising polypropylene;  
and

a second layer comprising an oxygen barrier material, directly adjacent to said first layer;  
at least one of the first and second layers further comprising an adhesive to facilitate bonding between the first and second layers, the container having been biaxially stretched and having a haze value of less than approximately 29% measured through a section of the container having a total thickness of greater than approximately 15 mils.

18. (Previously Presented) The container of claim 17 the first layer comprising the adhesive wherein said adhesive comprises approximately 0.01% to about 0.20% maleic anhydride.

19. (Previously Presented) The container of claim 17 the first layer comprising the adhesive wherein said adhesive comprises approximately 0.015% maleic anhydride.

20. (Cancelled)

21. (Previously Presented) The container of claim 17 wherein said container has a haze value of approximately 10%-12% measured through a section of the container having a total thickness of greater than approximately 15 mils.

22. (Previously Presented) The container of claim 17 wherein said second layer comprises EVOH.

23. (Previously Presented) The container of claim 17 wherein said second layer comprises nylon.

24. (Previously Presented) The container of claim 17 wherein said second layer comprises nylon 6.

25. (Previously Presented) The container of claim 17 wherein said second layer comprises nylon 6/66.

26. (Previously Presented) The container of claim 17, the adhesive being maleic anhydride.

27. (Previously Presented) The container of claim 17 further comprising a third layer comprised of polypropylene adjacent to the second layer.

28. (Previously Presented) The container of claim 27, the adhesive in one of the first and second layers being located in the first layer and the third layer further comprising adhesive.

29. (Previously Presented) The container of claim 28, the adhesive in the first and third layers being maleic anhydride.

30. (Previously Presented) The container of claim 27, the third layer defining an outermost layer.

31. (Previously Presented) The container of claim 30, the third layer being bonded directly to the second layer.

32. (Previously Presented) The container of claim 23, the second layer further comprising cobalt.

33.-153. (Cancelled)